



249 Laurel Road
Lexington, SC 29073
Ph: (866) 515-0965 Fax: (803) 343-1001
www.sterlingsand.com

Typical Analysis

#15 Coarse Sand

US Mesh	% Retained Per Sieve	Anchor Pattern	Material Uses
8	0.00		
12	17.90	2.0-4.0	Tanks, heavy rust, concrete, & stripping
16	76.00		
20	98.00		
30	100.00		
40	100.00	Min. Size Nozzle	
50	100.00	3/8"	
70	100.00		
100	100.00		
