



249 Laurel Road
 Lexington, SC 29073
 Ph: (866) 515-0965 Fax: (803) 343-1001
 www.sterlingsand.com

Typical Analysis

#25 Medium Sand

mm	US Mesh	% Passing Cummulative	% Retained Per Sieve	Anchor Pattern	Material Uses
2.06	8	99.97	0.03	1.5 -2.5	Medium rust, bridges, aggregate exposure, rust and paint stripping
1.18	16	92.76	7.21		
0.850	20	74.14	18.62	Min Size Nozzle	structural steel, tanks, mill scale general usages also used for traction
0.600	30	40.77	33.37		
0.425	40	14.37	26.40		
0.300	50	3.49	10.88		
0.212	70	0.54	2.95		
0.150	100	0.06	0.48		
0.106	140	0.00	0.06	1/4"	
0.090	200	0.00	0.00		
0.053	270	0.00	0.00		
<.053	PAN	0.00	0.00		
