



249 Laurel Road
 Lexington, SC 29073
 Ph: (866) 515-0965 Fax: (803) 343-1001
 www.sterlingsand.com

Typical Analysis

#45 Fine Sand

mm	US Mesh	% Passing Cummulative	% Retained Per Sieve	Anchor Pattern	Material Uses
2.060	8	0.00	0.00	1.0-1.5	Medium rust, bridges, aggregate exposure, rust and paint stripping structural steel, tanks, mill scale general usages also used for play sand
1.180	16	0.00	0.00		
0.850	20	97.49	2.51		
0.600	30	86.96	10.53		
0.425	40	61.19	25.77		
0.300	50	30.75	30.44		
0.212	70	10.91	19.84	Min Size Nozzle	
0.150	100	3.31	7.6		
0.106	140	1	2.31	3/16"	
0.090	200	0.38	0.62		
0.053	270	0.19	0.19		
<.053	PAN	0.00	0.00		
