



249 Laurel Road
 Lexington, SC 29073
 Ph: (866) 515-0965 Fax: (803) 343-1001
 www.sterlingsand.com

Typical Analysis

#55 X-Fine Sand

mm	US Mesh	% Passing Cummulative	% Retained Per Sieve	Anchor Pattern	Material Uses
2.060	8	100.00	0.00	0.5 - 1.0	High pressure blast system, smooth surfaces, trucks also used for play sand
1.180	16	100.00	0.00		
0.850	20	99.88	0.12		
0.600	30	98.20	1.68		
0.425	40	89.77	8.43		
0.300	50	66.61	23.16	Min Size Nozzle	
0.212	70	35.49	31.12		
0.150	100	12.08	23.41	1/8"	
0.106	140	1.99	10.09		
0.090	200	0.21	1.79		
0.053	270	0.03	0.18		
<.053	PAN	0.00	0.03		
