



249 Laurel Road  
Lexington, SC 29073  
Ph: (866) 515-0965 Fax: (803) 343-1001  
www.sterlingsand.com

### Typical Analysis

## #80 Ultra-Fine Sand

---

mm	US Mesh	% Passing Cumulative	% Retained Per Sieve	Material Uses
2.060	8	100.00	0.00	Powder coating and blasting glass
1.180	16	100.00	0.00	
0.850	20	99.97	0.03	
0.600	30	99.77	0.20	
0.425	40	97.44	2.33	
0.300	50	89.25	8.19	
0.212	70	69.13	20.12	
0.150	100	38.1	31.03	
0.106	140	13.64	24.46	
0.090	200	3.57	10.07	
0.053	270	0.55	3.03	
<.053	PAN	0.00	0.55	

---